



## PELICOAT PRO JET

Mass water repellent for injection against upward humidity

### Presentation :

PELICOAT PRO JET is an **exclusive mass water repellent** . After injection it constitutes an **EFFECTIVE AND DEFINITIVE BARRIER** against the rising of moist by capilarity .  
It is a complex formula basis of oligomeric siloxane resins renforced with an organometallic complex .

### Advantages :

- \* Protect durably against the rising of moist by capilarity .
- \* **Odorless** during and after the treatment .
- \* Ecologic and respect the environment .
- \* Neutralise salts at the level of draining barrier .
- \* Allow the wall breathe .

### Characteristics :

Constraint	:	PA + or - 20 ° C - 9,045
Aspect	:	Transparent and totally invisible liquid
Flash point	:	58 ° C close cup
Density at 25 ° C	:	0,85
Active materials contents	:	10 %
Viscosity	:	PA.S 2,24

### Application :

Bore on the inside or outside of the wall a row of **12 mm diameter** holes, approximately **10 cm** above ground ( preferably in the joint ) .

The holes must be bored to approx. 2/3 of the kickness of the wall and **spaced +/- 12 cm** .

**Inject PELICOAT PRO JET with a pressure of 5 to 8 kg/cm<sup>2</sup>**, 1,5 to 2 liters by linear meter .

The injection equipment must be equiped with a meter .

### Remark :

Waterproofing is obtained in +/- 48 hours

Drying out of the wall takes 2 to 6 months depending on inside or outside ambiance .